

AMENDMENT B
(37 C.F.R. 1.111)

IN THE CLAIMS:

Please amend claims 1 and 5 in accordance with 37 C.F.R. 1.121.

The claims are attached herein on separate sheets.

AMENDMENT TO CLAIMS

[Deleted material is struck-through and added material is underlined]

1. (Currently Amended) A Cu-Sn-O alloy plating having an oxygen content of 0.3 to 50 at% in the plating, **wherein said plating is applied to a substrate material selected from a group consisting of metal materials, ceramic materials, plastic materials, or ceramic or plastic materials on which a metal plating has been applied in advance.**
2. (Original) The Cu-Sn-O alloy plating as claimed in claim 1, wherein the oxygen content is 0.5 to 47 at%.
3. (Original) The Cu-Sn-O alloy plating as claimed in claim 1, wherein the oxygen content is 1.5 to 50 at% and the plating has blackish appearance.
4. (Previously Presented) The Cu-Sn-O alloy plating as claimed in claim 1, wherein a copper content is 20 to 80 at%, and a tin content is 10 to 70 at% in the plating.
5. (Currently Amended) An ornamental article having Cu-Sn-O alloy plating having an oxygen content of 0.3 to 50 at% in the plating, **wherein said plating is applied to said ornamental article and said ornamental article is made from material selected from a group consisting of metal materials, ceramic materials, plastic materials, or ceramic or plastic materials on which a metal plating has been applied in advance.**
6. (Original) The ornamental article as claimed in claim 5, wherein the article is a snap button.
7. (Previously Presented) The Cu-Sn-O alloy plating as claimed in claim 2, wherein a copper content is 20 to 80 at%, and a tin content is 10 to 70 at% in the plating.
8. (Previously Presented) The Cu-Sn-O alloy plating as claimed in claim 3, wherein a copper content is 20 to 80 at%, and a tin content is 10 to 70 at% in the plating.
9. (Previously Presented) The ornamental article as claimed in claim 5, wherein the oxygen content is 0.5 to 47 at%.
10. (Previously Presented) The ornamental article as claimed in claim 5, wherein the oxygen content is 1.5 to 50 at% and the plating has blackish appearance.
11. (Previously Presented) The ornamental article as claimed in claim 5, wherein a copper content is 20 to 80 at%, and a tin content is 10 to 70 at% in the plating.
12. (Previously Presented) The ornamental article as claimed in claim 9, wherein a copper content is 20 to 80 at%, and a tin content is 10 to 70 at% in the plating.

13. (Previously Presented) The ornamental article as claimed in claim 10, wherein a copper content is 20 to 80 at%, and a tin content is 10 to 70 at% in the plating.
14. (Previously Presented) The ornamental article as claimed in claim 9, wherein the article is a snap button.
15. (Previously Presented) The ornamental article as claimed in claim 10, wherein the article is a snap button.
16. (Previously Presented) The ornamental article as claimed in claim 11, wherein the article is a snap button.
17. (Previously Presented) The ornamental article as claimed in claim 12, wherein the article is a snap button.